Technical Datasheet



Vena® TECHNOSIL SAE J20R3 Class A

Ref: DO 03.10 FT 45. Rev. 07 Date: 10/09/2015



Applications

It is especially recommended for use in water and ethylene glycol-based engine coolant system applications.

For the automotive industry, the most common standard for coolant system hoses is SAE J20, which classifies them according to type of service. This reference, SAE 20R3, are for heater service.

This type of hoe is used in connecting heater systems and other components in the coolant circulating systems of ground vehicles (for example in heavy duty truck and bus engines).

Limitations

Respect the work pressure established values.

Gas oil and oil stains do not damage the tubes, but they should not be used to transport fuel or oil, nor be submerged in these liquids.

This product is not recommended for the transport of abrasive particles.

Regulations

- Meets or exceeds operating and dimensional requirements of SAE J20 R3 Class A.
- Silicone rubber used is in accordance with EU Directive 2002/95/ECC for Restriction of the use of hazardous substances (RoHS).

Properties

- Smooth inner and outer appearance, and blue color.
- Excellent resistance to thermal aging and oxidizing agents (oxygen, ozone, UV).
- Operational temperature range from -60°C (-75 F) to +180°C (356 F).
- The standard manufacturing length is 76 meters long (249.34 ft.), although it is available in shorter lengths if necessary.

Technical Specifications

Physical tests	Method	SAE Designation	Value	
Cold Flexibility (5hrs/	CAE 120 (E 1 2)	Not fracture,	Pass	
-40°C)	SAE J20 (5.1.2)	not show any cracks or breaks		
Ozone test	ASTM D-1149	Not show any	Pass	
(50ppcm/100hrs/40°C)	ASTINDITIO	cracks		
Kink test (%)	SAE J20 (5.1.4)	Collapse	<9	
MIIN LESE (70)	JAL J20 (5.1.4)	allowed 25%		

Technical Datasheet



Vena® TECHNOSIL SAE J20R3 Class A

Ref: DO 03.10 FT 45. Rev. 07 Date: 10/09/2015

Inner Diameter		Wall thickness		Working Pressure ISO 1402/2009		Bursting Pressure ISO 1402/2009		Vacuum Pressure	
mm	inch	±0.5mm	±0.02inch	Bar at 20°C	Psi at 68°F	Bar at 20°C	Psi at 68ºF	Bar at 20°C	Psi at 68°F
6.3	1/4	3.45	0.14	9.60	139.24	28.80	417.71	0.95	13.78
7.9	1/3	3.55	0.14	8.80	127.63	26.50	384.35	0.95	13.78
9.5	3/8	3.55	0.14	7.70	111.68	23.00	333.59	0.95	13.78
12.7	1/2	3.80	0.15	6.80	98.63	20.30	294.43	0.90	13.05
15.8	5/8	4.35	0.17	5.90	85.57	17.80	258.17	0.70	10.15
19.0	3/4	4.45	0.18	5.10	73.97	15.20	220.46	0.70	10.15
22.0	7/8	4.65	0.18	5.00	72.52	15.00	217.56	0.70	10.15
25.4	1	4.55	0.18	4.90	71.07	14.80	214.66	0.55	7.98
28.0	1 1/8	5.00	0.20	4.40	63.82	13.20	191.45	0.20	2.90
32.0	1 1/4	5.50	0.22	3.90	56.56	11.80	171.14	0.16	2.32

Construction

This reference is manufactured by extrusion with polyester yarn braiding inside the tube.